

Quality Coating

BROW – UNACCEPTABLE ON BOTTLE WHEN VISIBLE & ABLE TO FEEL SLIGHT RAISE WITH GLOVED HAND. BROW APPEARS AS A LARGE "SAG" IN COATING ON SIDE(S) OF BOTTLE.

BUBBLES – UNACCEPTABLE IF THE BUBBLE GOES THROUGH TO THE GLASS SURFACE. TEST WITH THE TIP OF A KNIFE. IF THE BUBBLE DOES NOT GO THROUGH TO THE GLASS, THEN IT IS ACCEPTABLE UP TO 1.5MM IN SIZE. LARGER BUBBLES ARE UNACCEPTABLE, AND NO BOTTLE SHOULD CONTAIN MORE THAN ONE BUBBLE 1.5MM IN SIZE, OR TWO OR MORE BUBBLES GREATER THAN 3MM IN SIZE COMBINED. BUBBLES THAT ARE FORMED FROM MOLDING MARKING IS ACCEPTABLE

DIRT/DEBRIS – ANY ONE DIRT PARTICLE ON BOTTLE GREATER THAN 1.5MM IN SIZE IS UNACCEPTABLE. MORE THAN ONE DIRT PARTICLE, BUT NO MORE THAN THREE IS ACCEPTABLE IF THE TOTAL, COMBINED SIZE OF DIRT PARTICLES IS NO MORE THAN 3MM IN SIZE.

RING STACKING SLITS- AS LONG AS THEY DO NOT GO THROUGH TO THE GLASS SURFACE IT IS ACCEPTABLE

DEFORMITIES OF GLASS-DEFORMITIES SUCH AS BIRD SWING AND OTHER OBVIOUS MOLDING FLAWS ARE UNACCEPTABLE

CRACKED/BROKEN BOTTLE – NO CRACKS AND/OR BREAKAGE, ANYWHERE ON BOTTLE, IS ACCEPTABLE.

BOTTOM SURFACE OF BOTTLE – SURFACE MUST BE UNIFORM ALLOWING BOTTLE TO SIT LEVEL ON FLAT SURFACE. NO RUNS, RAISED AREAS, OR RIPPILING OF PLASTIC COATING IS ALLOWED.

GLASS DOPE (WHITE OR BLACK) – NO GLASS DOPE IS ALLOWED IN BOTTLE. DOPE APPEARS AS BLACK, AND/OR WHITE, AND HAS THE APPEARANCE OF FOREIGN MATERIAL.

BLISTERS – NO BLISTERS ARE ALLOWED IN GLASS SURFACE WHICH ARE GREATER THAN 0.5MM IN SIZE. BLISTER WILL APPEAR AS BUBBLE IN THE GLASS, NOT IN THE COATING.